

Sukh

curable powder coating dispersion is present in the form of a sintered, partially crosslinked and/or dried layer.

4.(Amended) The film [as claimed in any] of claim[s] 1[to 3], [comprising at least one layer based on] wherein at least one of the one or more coating layers results from the application of a liquid coating[material].

*AB
cont.*

~~5. (Amended) The film [as claimed in any] of claim[s] 1[to 4], wherein the support layer to be coated with the one or more coating [materials] layers is selected from the group consisting of a plastic, [preferably a thermoplastic, or] a self-supporting paint film, and mixtures thereof.~~

6. (Amended) The film [as claimed in any] of claim[s] 1[to 5], wherein at least one of the one or more coating layers compris[ing]es[at least one layer of] a surfacer composition.

7. (Amended) The film [as claimed in any] of claim[s] 1[to 6], wherein a removable film has been applied to the at least one coating layer [based on] comprising a thermally curable powder coating [material] or a thermally curable powder coating dispersion.

8.(Amended) The film [as claimed in any] of claim[s] 1[to 7], wherein - the support layer has a thickness of from 10 to 1 000 μm , [preferably from 10 to 500 μm],

Subj

- the layer based on a liquid coating material has a thickness of from 15 to 200 μm , [preferably from 50 to 100 μm], and
the at least one coating layer [based on] comprising a thermally curable powder coating [material] or a thermally curable powder coating dispersion has a thickness of from 30 to 200 μm [, preferably from 50 to 100 μm].

AB Com

9. (Amended) A process for producing a coated film [as claimed in any] of claim[s] 1 [to 8], [which comprises] comprising applying a thermally curable powder coating [material] or a thermally curable powder coating dispersion to [the] a support layer or to [the] one or more layers [based on] comprising a liquid coating [material], partially sintering the thermally curable powder coating [material] or drying the thermally curable powder coating dispersion, and, if desired, applying a removable film.

10. (Amended) A molding coated with a film [as claimed in any] of claim[s] 1[to 8].

11. (Amended) A method of coating moldings, [which comprises] comprising applying a film [as claimed in any] of claim[s] 1[to 8] and [then] crosslinking the at least one layer [based] comprising [on] the thermally curable powder coating [material] or the thermally curable powder coating dispersion[, the crosslinking taking place preferably by means of heat supply or radiation].

1 2 3 4 5 6 7 8 9 10 11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99 100

Sch
52
AB
Cont

B

12. (Amended) ~~The use of a film as claimed in [any of] claim[s] 1[to 8] to coat moldings[, preferably vehicle bodies and domestic appliances].~~

AK
SEARCHED
INDEXED
MAILED

13. (New) The film of claim 2, wherein at least one member selected from the group consisting of the thermally curable powder coating, the thermally curable powder coating dispersion, and a polymer in the powder coating or the powder coating dispersion, has a melting point of from 70 to 100°C.

14. (New) The film of claim 5, wherein the support layer to be coated with the one or more coating layers is a thermoplastic.

15. (New) The film of claim 8, wherein

- the support layer has a thickness of from 10 to 500 μm ,
- the layer based on a liquid coating material has a thickness of from 50 to 100 μm , and
- the at least one coating layer comprising a thermally curable powder coating or a thermally curable powder coating dispersion has a thickness of from 50 to 100 μm .

16. (New) The method of claim 11 wherein crosslinking occurs by means of heat supply or radiation.

B

17. (New) ~~The use of a film as claimed in claim 1 to coat vehicle bodies and domestic appliances.~~